



Almond




Beaver Brown




Redwood



Royal Brown



Sandtone




Terra Bronze



Black



Buckskin




Victorian Gray



White



80 White




Wicker



Cameo



Charcoal Gray



Antique Ivory




Bronze



Herringbone




Country Blue



Classic Cream



Clay



Desert Sand



Everest



Copper Penny




Brookstone



Harbor Grey



Village Green



Evergreen



Linen



Musket Brown



Pebblestone Clay

## QUALITY ASSURANCE

American Construction Metals offers quality rainware products and accessories in a wide range of popular colors. Our rainware and accessory products are backed by a 20-year limited warranty, one of the best warranties in the industry.\*

\*See warranty for details.

Colors shown may vary slightly from actual material.

valspar

American Construction Metals Rainware Systems are finished with Valspar Polykote® 3000 coatings. Polykote® 3000 is a field proven coating for multiple purpose polyester finishes designed for a wide range of applications. They are applied to long life products: such as rain carrying equipment, trim coil, and awnings. The reliable adhesion and flexibility properties of Polykote® 3000 provides superior post forming performance to enhance the coated product's appearance and durability for years to come.

### Typical Physical Properties of Polykote® 3000 Coatings(A)

PROPERTIES	RESULTS	TEST DESIGNATION
Pencil Hardness	F - 2H	ASTM D-3363
Flexibility	1 - 2T	ASTM D4145
Surface Appearance	Smooth	
60° Specular Gloss	±5% of Customer Specification	ASTM D523
Solvent Resistance	Acceptable(B)	ASTM D5402
Adhesion		
Impact	Acceptable(C)	ASTM D2794
Cross Hatch	Acceptable(D)	ASTM D3359
ACCELERATED TESTS		
QUV Resistance 800 Hours	Acceptable(E)	ASTM G-53
Humidity 1,000 Hours Exposure at 100°F and 100% Humidity	Acceptable(F)	ASTM D-2247
Salt Spray 250-1,000 Hours 5% Salt Fog at 95°F	Acceptable(G)	ASTM B-117

Notes:

(A) Applied in accordance with Valspar technical specification sheet on properly cleaned and pretreated metal surfaces.

(B) Total system flexibility varies with basecoat selection.

(C) Aluminum withstands impact weight of 1.5 x Metal Gauge without loss of adhesion.

(D) No loss of adhesion between coating and substrate to point of metal rupture with 1/8" cross hatch scribe pattern through coating to bare metal.

(E) No objectionable loss of gloss, blistering, cracking, chalking or color change.

(F) Aluminum - no blisters or loss of adhesion.

(G) The number of hours tested varies by substrate and/or primer selected. Aluminum - no field blistering, no more than 1/32" creep from the scribe after 1,000 hours exposure.

RAINWARE Color Palette



Houston, TX